



The Industry Standard Spray Wash Detergent









Aqueous degreasing chemistry developed for soil removal during the manufacturing or rebuild of Aerospace components in inline or cabinet type spray wash cleaning processes. Mildly alkaline solution with excellent particulate removal abilities. AquaVantage 1990 GD is a free rinsing solution providing a water break free surface. Safe on virtually all metals. AquaVantage 1990 GD is noncorrosive and will not stain metals.

- Independent Performance Documentation Proven Cleaning Results
- Water-Based, Dilutable Formulation Dilutes specific to your application
- Extends Bath Life Creates Labor Savings & Reduces Costs
- In-Process Corrosion Control
- Low Foaming at Temperatures Greater Than 120°F (49°C)
- Free Rinsing Cleaner Parts & Simplified Cleaning
- **Reduced Cleaning Rework & Rejects**
- No Hazardous Ingredients as listed on the SDS (w/OSHA PELS)
- SCAQMD: Certified as a Clean Air Solvent
- Separates oil effectively for easy skimming
- **RoHS Compliant**

Industry Approvals & Conformance

- Airbus: AIPI 09-01-003 Approved Alkaline Cleaner
- Airbus UK: ABP 8-1290; Approved Alkaline Cleaner Boeing: BAC 5763; Emulsion Cleaning
- Boeing: HP 9-25; Degreasing
- General Dynamics, Electric Boat Division: Contract No. N0024-95-C-2103
- GE Aviation: S-421
- **GE Aviation:** List of Alloy Compatible Cleaners
- GM: FID Number 330546
- Goodrich: ML21345; Cleaning Aluminum and Steel **Brake/Wheel Parts**
- Hamilton Sundstrand: Soak Cleaning of Heat Exchangers
- Honeywell (Allied Signal): EMS 53170; Steel Brake/ Wheel Parts
- Honeywell: Standard Practices Manual
- Lockheed Martin: EPS G32.0160
- Lockheed Martin: LMA-PG006, Rev B
- Lucas Aerospace: DC Starter/Gen
- **National Aeronautics and Space Administration:** Procedures for Cleaning of Systems and Equipment for Oxygen Service

Test Compliance

- ARP 1755A: Stock Loss (Cat. 9)
- ARP 1755B: Stock Loss (Cat.10)
- ASTM F-483: Total Immersion Corrosion
- ASTM F-484: Stress Crazing of Acrylic Plastics
- ASTM F-485: Unpainted Aircraft Surfaces ASTM F-502: Painted Aircraft Surfaces
- ASTM F-519: Hydrogen Embrittlement (Type 1c)
- ASTM F-945: Titanium Stress Corrosion (AMS 4916 & 4911 Alloys)
- ASTM F-1110: Sandwich Corrosion
- ASTM F-1111: Low-Embrittling Cadmium Plate
- Boeing: D6-17487 Rev. K; Exterior Cleaner
- Boeing (McDonnell Douglas): CSD 1; General Purpose Cleaner
- **Contains No Cyanides or Sulfides**
- GE Aviation: CT-882; Solvent Replacement
- **Sandwich Corrosion Test**

- National Stock Number: 05 Size; 6850-01-428-8842
- National Stock Number: 55 Size; 6850-01-435-6459
- Philips Electronics: 12NC Number: 1322-529-81201 Rolls-Royce: CSS204 Class A
- Rolls-Royce: OMAT 1/24 AG
- SAFRAN: PR-1500
- Teledyne Ryan Aeronautical: RACO 2833, Alkaline Degreasing Fluid, Spray
- United Airlines: UMS CLE3005-3-2-Cleaner, High Temp/High Press. A/C Parts Washer

TANK MAINTENANCE

Proper maintenance of your immersion/ultrasonic tank or spray wash system will ensure the longest possible detergent bath life, the best part cleaning performance and the optimal assurance against part corrosion.

BHC has developed Maintenance Guidelines for Aqueous Detergent Tanks, a comprehensive flow chart to illustrate the process and a step-by-step video to guide you through.



an Tank Maintenance

Concentration Verification for AquaVantage 1990 GD

Brulin Titration Kit	(Prod. No. XTRKIT)
Sample Size:	20 mL
Titrant:	1.0 N HCl Solution
Indicator:	Bromophenol Blue (4 Drops)
Concentration %:	Drops Titrant x 0.34

quaramage root al		
Burette Test Method		
Sample Size:	25 mL	
Titrant:	0.1 N Acid Solution	
Indicator:	3.80	
Concentration %:	mL Titrant x 0.80	
or		
Sample Size:	25 mL	
Titrant:	0.1 N Acid Solution	
pH Endpoint:	4.50	
Concentration %:	mL Titrant x 0.86	



AquaVantage®



1990 GD

Performance Properties

Substrates

AquaVantage 1990 GD is non-corrosive and non-staining to a wide variety of alloys. Some selected categories of materials compatible with AquaVantage 1990 GD include*:

Ferrous Metals: Carbon Steel • Stainless Steel • Steel

Non-Ferrous Metals & Alloys: Aluminum • Cadmium Plating • Chrome Plating • Copper (Alloys & Plating) • Magnesium & Magnesium Alloys • Nickel, Nickel Alloys & Plating

• Titanium & Titanium Alloys

Plastic & Composites: Acrylics • High Density Polyethylene/HDPE • Nitrile Butadiene Rubber • Polyvinyl Chloride/PVC • Rubber

Other: Painted Surfaces

Soils

AquaVantage 1990 GD removes a wide range of organic and inorganic soils. Some categories of soils that can be removed with AquaVantage 1990 GD include*: Buffing Compounds • Coolants • Dirt (Particulate) • Fat • Grease • Oil (General, Cutting, Drawing Compounds, Forming, Hydrocarbon, Lubricants, Self Emulsifying, Water Soluble)

* Material compatibility should always be confirmed via testing with specific contaminants under specific cleaning conditions.

Use Recommendations

Spray Wash Systems (Batch or Continuous)
3-15%, typically used at 5% Minimum recommended concentration for cleaning aluminum is 5.0%
120-170°F (49-77°C); typically used at 130-150°F (54-66°C)
1-30 minutes: typical parts are clean in 3-10 minutes
A heated rinse may improve overall performance. Some OEM process specifications may require a heated rinse.
Recommended conductivity of final rinse water: • Ultra-Clean Applications: ≤ 50 microsiemens • Precision Cleaning: ≤ 500 microsiemens • Gross Cleaning: > 500 microsiemens

Authorized Representative:

Typical Chemical Characteristics

**	
Physical Form	Liquid
Color	Slight Yellow
Odor/Fragrance	Mild
Viscosity	Water-thin
Weight	8.88 lbs/gal (1.06 g/ml)
pH of Concentrate	11.3
pH of Working Solution	10.5
Flash Point (PMCC)	None to boiling
Foaming Tendency	Low
Calculated V.O.C	0% (0 g/l)
Freeze/Thaw	Reusable after thawing & remixing

Shipping: Non-hazardous for shipping by ground, sea, or air in all package sizes.

Storage: Store in well-ventilated areas at temperatures between 40-110°F (4-43°C). The recommended shelf life of this product is 18 months.

Disposal: Dispose of waste and residues in accordance with local authority requirements. Please recycle container.

Prevention: Wear safety glasses with side shields (or goggles). Wear protective gloves. Wash hands thoroughly after handling.

Product Number: 301008 (Formerly Brulin 1990 GD)

Availability:

- 5 Gal (19L)
- 55 Gal (208L)
- 275 Gal Tote (1,041L)
- Bulk up to 5,000 Gal (~19,000L)

BHC offers a full line of Brulin-branded industrial chemicals for industries such as Space & Aerospace, Automotive, Precision Metal, Medical and Optics.



317.923.3211 WWW.BHCINC.COM ISO 9001:2008 CERTIFIED Made in the USA

